



Product Code: Enkilon 1026

PTFE Compound: Enkilon Polyimide filled PTFE

Typical Properties*

Properties	Standard	Units	Non-Free Flow Grade (NFF)	Free-Flow Grade (NFF)
Tensile Strength	ISO 13000-2	MPa	1.75 - 1.85	1.75 - 1.85
% Elongation	ISO 13000-2	%	Min 14	Min 11
Specific Gravity	ISO 13000-2	-	Min 150	Min 130
Hardness	Needle	Shore D	60-65	60-65

*These figures are typical values for the material and do not represent a product specification. Properties will vary depending on the source of raw material, method of processing, physical form of the product, direction of measurement etc. It is intended only as a guide for use at your risk and discretion. Prior to any application the above product has to be tested and accepted by the processor.

Safety toxicology

This product is a fluoropolymer material and related precautions should be followed when handling and processing.