



Product Code: ANU 330

Material: 30% Carbon Fibre Filled PEEK Powder

Recommended Processing Route: Compression molding

Typical Properties*

Properties	Standard	Units	Powder Grade
Tensile Strength	ASTM D638**	MPa	120
% Elongation	ASTM D638**	%	3
Specific Gravity	ASTM D792	-	1.4-1.5
Hardness	Needle	Shore D	85-95

*These figures are typical values for the material and do not represent a product specification. Properties will vary depending on the source of raw material, processing parameters, physical form of the product, direction of measurement etc. It is intended only as a guide for use at your risk and discretion. Prior to any application the above product has to be tested and accepted by the processor.

** Modified ASTM D638 Test Method.